

# 841AR Liquid



## Super Shield™ Nickel Conductive Paint

841AR is a conductive paint that consists of a 1-part, solvent-based acrylic lacquer, pigmented with a highly conductive nickel flake. It is smooth, hard, and abrasion resistant. It can be easily applied by brush or spray. It has a quick dry time, with no heat cure necessary. It adheres strongly to most injection molded plastics, such as ABS, PBT, PVA and ABS/PC blend. It also provides strong corrosion resistance and is suitable for use in marine environments.

841AR provides a conductive coating for the interior of plastic electronic enclosures that suppresses EMI/RFI emissions.



## Features & Benefits

- UL Recognized (File # E202609)
- Provides effective EMI/RFI shielding over a broad frequency range
- Strong corrosion resistance
- Mild solvent system, safe on polystyrenes
- Does not contain toluene, xylene, or MEK
- Also available in aerosol (841AR-340G) and pen (841AR-P) formats, see separate TDSs

## Available Packaging

Cat. No.	Packaging	Net Vol.	Net Wt.
841AR-15ML	Jar	12 mL	20.2 g
841AR-150ML	Can	150 mL	253 g
841AR-900ML	Can	850 mL	1.43 kg
841AR-3.78L	Can	3.60 L	6.07 kg

## Cured Properties

Resistivity	4.0 x 10 <sup>-3</sup> Ω·cm
Surface Resistance @ 50 µm	0.68 Ω/sq
Salt fog @ 35 °C [95 °F], 96 h	Excellent
Service Temperature Range	-40–120 °C

## Usage Parameters

Recoat Time	3 min
Cure Times	24 h @ 22 °C 30 min @ 65 °C
Recommended Film Thickness	50 µm
Minimum Film Thickness	40 µm
Theoretical Coverage @ 2 mil (based on 100% transfer efficiency)	44 785 cm <sup>2</sup> /L

## Uncured Properties

Viscosity @ 25 °C	1 460 cP
Density	1.70 g/mL
Percent Solids	57 %
Shelf Life	3 y
Calculated VOC	236 g/L



sales@chilternconnections.co.uk  
+44 (0) 1491 824 788

www.chilternconnections.co.uk

# 841AR Liquid



## Application Instructions

Read the product SDS and Application Guide for more detailed instructions before using this product (downloadable at [www.mgchemicals.com](http://www.mgchemicals.com)).

## Recommended Preparation

Clean the substrate with Isopropyl Alcohol, MG #824, so the surface is free of oils, dust, and other residues.

## Recommended Thinner

When applying to polycarbonate or ABS, thin with MG #4351 Thinner 1. For other substrates, use MG #435 Thinner.

## Brush

Thinning is not required for most brush applications. Use a foam brush or MG #855 horse hair brush.


## Manual Spray Guns

Dilute 1-part paint with 1-part thinner. Use a standard fluid nozzle gun to spray the diluted paint. The settings listed below are recommendations; however, performance will vary with different brands:

	LVMP	HVLP
Nozzle tip diameter	1.2–1.4 mm	1.2–1.4 mm
Inlet pressure	5–15 psi	5–15 psi
Air flow	10–15 SCFM	8.3 SCFM
Air cap	5–10 psi	5–10 psi


When using a pressure pot and agitator, keep the agitator at low mixing speed with air pressure of 20–50 psi. Use the lowest pressure necessary to keep the particles suspended.

## Shielding Attenuation



Test performed with a two-coat thickness.

## Surface Resistance by Paint Thickness



## Selective Coating

For higher volume applications, paint can be applied via selective coating equipment. Use a system with constant fluid recirculation to keep the particles from settling in the lines. A fluid nozzle ranging from 1.2 mm–1.4 mm diameter and 5–10 psi fluid pressure is recommended depending on nozzle size. Thin the paint to adjust the viscosity to the level appropriate for the valve being used.

## Cure Instructions

Allow to dry at room temperature for 24 hours, or after letting sit for 3 minutes, cure the paint in an oven for 30 minutes @ 65 °C.

## Clean-up

Clean spray system and equipment with MEK or acetone, MG # 434.

## Storage and Handling

Store between -5 and 40 °C in a dry area, away from sunlight (see SDS).

## Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.



[sales@chilternconnections.co.uk](mailto:sales@chilternconnections.co.uk)  
+44 (0) 1491 824 788

[www.chilternconnections.co.uk](http://www.chilternconnections.co.uk)

12 October 2023 / Ver. 5.1

2