

Blue, Grey

Grounding & Cleaning

If the material is used on top of an already properly grounded surface, grounding hardware may not be necessary. Where no properly grounded surface is available, grounding hardware is required to provide a path-to-ground. Rg compliance verification measurements must be made per EN 61340-5-1 periodically with a surface resistance meter.

See Tech Bulletin TB-7000 for Reztore® Surface & Mat Cleaner Application Instructions.

Limited Lifetime Warranty:

Desco Europe warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by Desco Europe Limited Warranty.

RoHS 3, REACH, and Conflict Minerals Statement See the Desco Europe RoHS 3, REACH, and Conflict Minerals Statement:

DescoEurope.com/ROHS.aspx

See the Desco Europe Limited Warranty: DescoEurope.com/Limited-Warrantv.aspx

See the Desco Europe Disclaimer: DescoEurope.com/Disclaimer.aspx



Standard Document Meets Requirements of:

EN 61340-5-1 Working Surface

Electrical Properties

Property Test Method Value

Rg Resistance: IEC 61340-2-3 1×10^6 to $< 1 \times 10^8$ ohms Rp-p Resistance: IFC 61340-2-3 1×10^6 to $< 1 \times 10^8$ ohms

Physical Properties

Construction: Heat fused vinyl composite

Thickness: 3.2mm Colour:* Blue, grey Texture:* Light Embossing

45 Shore "A", per ASTM-D412 Hardness:

Greater than 21.1 Kg/cm², per ASTM-D412 Greater than 36 Kg/ cm², per ASTM-D624 Tensile Strength: Tear Strength: Greater than 80%, per ASTM-D412 Elongation: Abrasion Resistance: Greater than 750 cycles, per Tabor-CS17

Heat Resistance: -28.9°C to 60°C continuous

Chemical Resistance: Resistance to degradation by inorganic acids,

organic acids, reducing agents, aliphatic hydrocarbons, mineral

oil, aldehydes, and amines

Tolerances:

Width ± 0.250"

Length ± 0.250" every 1 linear foot of running material.

Thickness ±10%

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.

*Colour, texture, and gauge may vary between lots and mills

For product listings, please click Here.

Statfree Z2™ Material, Vinyl, Dissipative, 3 Layer, 3.2mm



DESCO EUROPE 2A DUNHAMS LANE, LETCHWORTH GARDEN CITY, HERTFORDSHIRE, SG6 1BE, UK PHONE: +44 (0) 1462 672005

E-MAIL: Service@DescoEurope.com, INTERNET: DescoEurope.com

Drawing Number PME-Z2

DATE: September 2017